



Clock Spring[®]

The Clock Spring composite repair sleeve and reinforcement system is uniquely designed for high pressure transmission pipelines. Made up of a pretensioned and pre-cured unidirectional e-glass composite coil, a high-modulus filler material, and a high lap-shear strength methyl methacrylate adhesive, it is proven to 8000 psi burst pressure, has a design life of beyond 50 years, and an installation history of more than 30 years, qualifying it as the first permanent repair in the industry.

Each Clock Spring coil is made up of 8 layers, providing a repair with a higher failure pressure than the original pristine pipe. Designed to structurally reinforce and permanently restore external anomalies to beyond original pipe strength, the Clock Spring sleeve can repair a broad range of metal loss up to 80% depth, deformation and mechanical damage, and mill defects. Clock Spring is available in 4-inch through 56-inch diameter kits.

APPLICATIONS

- Corrosion
- Gouges
- Dents
- Manufactured Defects

COMPLIANT WITH:

(standards/regulations)

- US DOT CFR 192 and 195
- CSA Z662
- ASME PCC-2 Article 401
- ISO 24817

BENEFITS:

- Installs without disrupting operations
- Two hours to backfill from installation
- Enhances short-term and long-term safety
- Marking band system makes repairs visible to in-line inspection tools
- No environmental hazards
- Easy transportation to site and no special tools to install
- No hot work or heavy lifting
- Can be installed underwater
- Available in high-temperature system



QUALIFICATION DATA

PROPERTIES	VALUE
Nominal Thickness	0.065 inch (1.6 mm)
Complete 8-Layer System	0.5 inch (13 mm)
Width	12 inches +/- 0.5 inches (305 mm)
Lap Shear Strength	>1,200 psi (8.27 MPa)
Compressive Strength	>12,500 psi (86.18 MPa)

RESINS & ACTIVATORS	COILS & ACCESSORIES
Shelf Life: 12 months from manufacturing date. Following the ideal storage temperatures.	Store in a cool, dry area.
Storage: Do not freeze. Shelf life is based on continuous storage between 50°F (10°C) and 72°F (22°C) . Long term exposure above 72°F (22°C), will reduce the shelf life of these materials. Prolonged exposure above 95°F (35°C) quickly diminishes the reactivity of the product and should be avoided. Keep container tightly closed (do not open until ready to use). For industrial use only.	Do not store in direct sunlight.

HISTORY

The Clock Spring sleeve was the subject of an extensive 10-year research and development program and was the pioneer for the approval of composite repairs across the industry. It is the most tested, investigated, and documented composite repair solution ever developed and has earned its place as the industry's most trusted composite repair system. Clock Spring sleeves have been installed in more than 75 countries in practically every environment for more than three decades.

WARRANTY CSNRI routinely implements product improvements. Please contact your local distributor or office for the most current product specifications. CSNRI warrants the quality of this product when used according to directions.

PS_1022

ISO 9001 Certified

sales@libertysales.net
(877)373-0118

