() CSNRI° SnapWrap™

SnapWrap[™] is a multi-layered system of high strength, corrosion-resistant fiberglass that forms a composite split sleeve. Designed for repair and reinforcement in tight quarters, on pipe that is difficult to access, and on subsea pipe, it is installed with a high-performance adhesive and filler material. The split sleeves are available in ³⁄₄ inch to 56inch diameter and can be applied quickly and easily even in challenging environments, such as underwater, in splash zones, and on pipe racks with limited clearance.

APPLICATIONS:

- Tight access areas
- Process piping
- Subsea and offshore risers
- Low-pressure lines <1,000 psi
- Local distribution and terminal pipelines



COMPLIANT WITH:

(standards/regulations)

- ASME B31G, B31.4 & B31.8
- ASME PCC-2 Article 4.1, 4.2
- API 570 Section 8.1.4
- Non-welding Repairs (On-Stream)

BENEFITS:

- Eliminates unplanned down time
- Extends the life of aging and corroding assets
- Prevents future external corrosion
- No pipe cutting or welding
- No special tools to install
- No environmental hazards
- No hot work

SnapWrap[™]

QUALIFICATION DATA

PROPERTIES	VALUE	
Nominal Thickness	0.065 inch (1.6 mm)	
Complete 8-Layer System	0.5 inch (13 mm)	
Width	12 inches +/- 0.5 inches (305 mm)	
Lap Shear Strength	>1,200 psi (8.27 MPa)	
Compressive Strength	>12,500 psi (86.18 MPa)	
RESINS & ACTIVATORS		COILS & ACCESSORIES
Shelf Life: 12 months from manufacturing date. Following the ideal storage temperatures.		Store in a cool, dry area.
Storage: Do not freeze. Shelf life is based on continuous storage between 50°F (10°C) and 72°F (22°C). Long term exposure above		Do not store in direct sunlight.

WARRANTY CSNRI routinely implements product improvements. Please contact your local distributor or office for the most current product specifications. CSNRI warrants the quality of this product when used according to directions.

PS_1122

ISO 9001 Certified



72°F (22°C), will reduce the shelf life of these materials. Prolonged exposure above 95°F (35°C) quickly diminishes the reactivity of the product and should be avoided. Keep container tightly closed (do

not open until ready to use). For industrial use only.

