

# DENSOTHERM TAPE

## Hot Applied Pipeline Tape

### Description

Densotherm Tape is a hot applied bituminous tape and is suitable for use above or below ground. It is comprised of a non-woven synthetic fabric fully impregnated and coated with a flexible, high melting point bitumen compound. The tape is applied with the aid of a propane gas torch.

### Uses

- Used to protect pipes, fittings, welds, and bends

### Features

- Excellent adhesion to pipe and self
- Excellent resistance to cathodic disbonding
- Good impact resistance
- Good conformability
- Hot applied
- Compatible with common pipe coatings

### Application

Remove dirt, grease, and oil in accordance with requirements of SSPC-SP-1, "Solvent" Cleaning. Remove weld spatter, sharp points, and edges. Remove loose rust, paint and foreign matter by hand and/or power tool cleaning in accordance with SSPC-SP-2, or SP-3, "Hand Tool Cleaning" respectively. Apply a thin film of Denso Primer D to all surfaces to be wrapped and allow to dry. Begin wrapping using a reverse spiral wrap, at the same time, apply a flame torch to the side of the tape that is in contact with the surface. The side of the tape with the backing shall be facing away from the pipe. Then, apply slight heat to form a glass-like texture to the outside (backing) of tape during wrapping and at the completion of wrapping. The backing will melt away which indicates the proper heat. A minimum 1" (25mm) overlap should be used. For severe environments, a 55% overlap is recommended.



# TECHNICAL DATA SHEET

## Packaging

Tape Width	Rolls*/ Case	Coverage with 1" (25 mm) Overlap	Coverage with 55% Overlap
in.	ea.	ea.	ea.
2" (50 mm)	12	45 ft <sup>2</sup> /case (4 m <sup>2</sup> /case)	45 ft <sup>2</sup> /case (4 m <sup>2</sup> /case)
4" (100 mm)	6	75 ft <sup>2</sup> /case (7 m <sup>2</sup> /case)	45 ft <sup>2</sup> /case (4 m <sup>2</sup> /case)
6" (150 mm)	4	82 ft <sup>2</sup> /case (7.6 m <sup>2</sup> /case)	45 ft <sup>2</sup> /case (4 m <sup>2</sup> /case)
12" (300 mm)	2	90 ft <sup>2</sup> /case (8.4 m <sup>2</sup> /case)	45 ft <sup>2</sup> /case (4 m <sup>2</sup> /case)

\*All rolls are 50 feet (15 m) in length.

## Tech Data

Properties	Imperial	Metric
<b>Thickness</b> (ASTM D1000)	79 mils	2.0 mm
<b>Weight</b>	.41 lbs/ft <sup>2</sup>	2.0 kg/m <sup>2</sup>
<b>Breaking Strength</b> (ASTM 1000)	51.4 lbf/in.	9 N/mm
<b>Tear Strength</b> (ASTM 1004)	11.2 lbf	50 N
<b>Elongation @ Break</b>	12%	12%
<b>Adhesion Peel Strength</b> (ASTM D1000)		
To Primed Steel	13.7 lbf/in.	2.4 N/mm
To Self	13.7 lbf/in.	2.4 N/mm
<b>Impact Strength</b> (ASTM G-14)	5.9 ft lb	8.0 Nm
<b>Dielectric Strength</b>	20 kV	20 kV
<b>Maximum Service Temperature</b>	122°F	50°C
<b>Recommended Holiday Test Voltage</b>		
Single Layer	10 kV	10 kV
Double Layer	14 kV	14 kV
<b>Roll Widths</b>	2" to 12"	50 to 300 mm
<b>Roll Length</b>	50 ft	15 m
<b>Recommended Primer</b>	Denso Primer D	



DENSO, INC.

## LIBERTY SALES & DISTRIBUTION



**PHONE:** (877) 373-0118  
**FAX:** (888) 850-3787  
**EMAIL:** [sales@libertysales.net](mailto:sales@libertysales.net)  
**WEB:** [www.libertysales.net](http://www.libertysales.net)

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.