### PRODUCT DATA SHEET

# DENSYL TAPE

#### **All Purpose Petrolatum Tape**

# **Description**

Densyl Tape is composed of a non-woven synthetic fabric carrier, fully impregnated with a neutral compound based on saturated petrolatum and inert siliceous fillers.

#### Uses

Densyl Tapes are designed to withstand extreme temperature variations. The tapes provide long term corrosion protection to pipes, flanges, valves and related surfaces.

#### **Features**

- Meets NACE RP0375-2006
- Applied to marginally prepared surfaces (SSPC SP 2-3)
- · Conforms to irregular shapes and profiles
- · UV resistant
- · Can be applied to cold, wet surfaces
- · Not effected by water, acid, salts or soil organics
- · Encapsulation of lead paint
- · Contains no solvents
- · Easy application from arctic to tropical temperatures
- · Ready for immediate service after application
- Meets AWWA C217 Standard
- · Over an 80 year history of proven applications
- · Can be applied above and below ground
- · CSA Z245.30 compliant

## **Application**

Prepare surfaces by removing all loose scale, rust or other foreign matter in accordance to SSPC SP2 "Hand Tool Cleaning" or SP3 "Power Tool Cleaning". High pressure water wash of 3,000 - 7,000 psi (20.68 - 48.26 MPa) is also suitable. Apply a thin film of Denso Paste, which serves as a primer. Spirally wrap the tape with a minimum 1" (25 mm) overlap. For severely corrosive environments, a 55% overlap is recommended. While wrapping, press air pockets out and smooth all lap seams. For additional mechanical protection, an overwrap may be used to increase impact strength and electrical resistance.

Irregular surfaces such as valves, flanges, etc. may require the use of Densyl Mastic or Denso Profiling Mastic. Refer to the product sheets for these specific products for information on application and selection.



# **Densyl Tape**

Properties	English	METRIC
Thickness (ASTM D1000)	46 mils	1.15 mm avg.
Weight	.295 lbs/ft <sup>2</sup> .	1.44 kg/m² avg.
Breaking Strength (ASTM 1000)	22.5 lbf/in.	200 N/50 mm min
Water Vapor Transmission		
(ASTM E96 - 66 Procedure A)	0.006 perms avg.	0.006 perms avg.
Elongation @ Break	10% avg.	10% avg.
Breakdown Voltage (55% overlap)	16 kV min.	16 kV min.
Resistance to Cathodic Disbonding		
(ASTM G-8 - 30 days)	.28 in² avg.	180 mm² avg.
Resistance to Acids, Alkalies and Salts	Excellent	Excellent
Maximum Service Temperature	158°F	70°C
Roll Widths	2" to 12"	50 to 300 mm
Roll Length	33 ft	10 m
Recommended Primer	Dense	o Paste
	Denso Paste S105	

Quantity Estimates				
Tape Width	Rolls*/ Case	Coverage with 1" Overlap	Coverage with 55% Overlap	
in.	ea.	ea.	ea.	
2" (50 mm)	36	87 ft <sup>2</sup> /case (8.08 m <sup>2</sup> )	87 ft <sup>2</sup> /case (8.08 m <sup>2</sup> )	
4" (100 mm)	18	145 ft <sup>2</sup> /case (13.47 m <sup>2</sup> )	87 ft <sup>2</sup> /case (8.08 m <sup>2</sup> )	
6" (150 mm)	12	162 ft <sup>2</sup> /case (15.05 m <sup>2</sup> )	87 ft <sup>2</sup> /case (8.08 m <sup>2</sup> )	
8" (200 mm)	8	150 ft²/case (13.94 m²)	77 ft <sup>2</sup> /case (7.15m <sup>2</sup> )	
12" (300 mm)	6	177 ft <sup>2</sup> /case (16.44 m <sup>2</sup> )	87 ft <sup>2</sup> /case (8.08 m <sup>2</sup> )	



**DENSO NORTH AMERICA** 

A Member of Winn & Coales International

#### LIBERTY SALES & DISTRIBUTION

2880 Bergey Road, Suite F, Hatfield, PA 19440 19 West Maiden Street, Washington, PA 15301 Phone: (877) 373-0118 Fax: (888) 850-3787

Email: sales@libertysales.net Web: www.libertysales.net

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.