### PRODUCT DATA SHEET

# DENSO GLASS OUTERWRAP

#### **Protective Fiberglass Outerwrap**

### **Description**

Denso Glass Outerwrap is a fiberglass cloth impregnated with a water activated resin that is used as a protective outer wrap over Denso Petrolatum Tape.

#### Uses

A protective coating which offers exceptional mechanical and impact strength for underwater, underground, and above ground pipe and piles.

#### **Features**

- · Resists cold and hot temperatures
- · Easy to apply, no mixing or messy clean up
- · Resistant to water, acid, salts, or soil organics
- · Can be applied underwater or to wet surfaces
- · Minimal surface preparation required
- · Quick, long term protective coating, ready for immediate service
- · Contains no solvents
- · Can be top coated for aesthetics
- CSA Z245.30 component

### **Application**

Prepare surfaces by removing all loose scale, rust or other foreign matter in accordance to SSPC SP2 "Hand Tool Cleaning" or SP3 "Power Tool Cleaning". High pressure water wash of 3,000 - 7,000 psi (20.68-48.26 MPa) is also suitable. Spirally wrap a layer of Denso Petrolatum Tape with a minimum 1" (25 mm) overlap. For severely corrosive environments, a 55% overlap is recommended. While wrapping, press air pockets out and smooth all lap seams. Using rubber gloves, remove the Denso Glass Outerwrap from the hermetically sealed foiled pouch and soak in temperate water (salt or fresh) for 20 to 30 seconds. Remove and begin wrapping tightly, overlapping a recommended 50%.

Irregular surfaces such as valves, flanges, etc. may require the use of Densyl Mastic or Denso Profiling Mastic. Refer to the product sheets for these specific products for information on application and selection.



## **Denso Glass Outerwrap**

Property Specifications			
Properties	English	Metric	
Thickness	11 mils avg.	0.28 mm	
Flexural Strength (ASTM D790)	26,100 psi	183,501 Kgs/mm <sup>2</sup>	
Tensile Strength (ASTM D638)	36,000 psi	253,105 Kgs/mm <sup>2</sup>	
Compression Strength (ASTM D695-77)	26,600 psi	187,024 Kgs/mm²	
Dielectric Strength (ASTM D149)	16,000 volts	16,000 volts	
Impact Resistance (ASTM G14/ G62)	123 ft. lb.	167 Joules	
Maximum Service Temperature	250°F	121°C	
Setting Time			
@ 70°F (21°C)	30 minutes	30 minutes	
@ 90°F (32°C)	15 minutes	15 minutes	

<b>Quantity Estimates</b>				
Tape Width	Roll Length	Rolls*/ Case	Coverage with 50% Overlap	
in.	ea.	ea.	ea.	
3" (75 mm)	9' (2.7 m)	15	17 ft²/case (1.6 m²/case)	
4" (100 mm)	30' (9 m)	5	25 ft <sup>2</sup> /case (2.3 m <sup>2</sup> /case)	
8" (200 mm)	40' (12 m)	3	40 ft <sup>2</sup> /case (3.7 m <sup>2</sup> /case)	

SHELF LIFE: 24 months



#### **DENSO NORTH AMERICA**

A Member of Winn & Coales International

#### LIBERTY SALES & DISTRIBUTION

2880 Bergey Road, Suite F, Hatfield, PA 19440 19 West Maiden Street, Washington, PA 15301 Phone: (877) 373-0118 Fax: (888) 850-3787 Email: sales@libertysales.net Web:www.libertysales.net

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.