

# DENSO GLASS OUTERWRAP UV™

## UV Protective Fiberglass Outerwrap

### Description

Denso Glass Outerwrap UV is a fiberglass cloth impregnated with a water-activated, aliphatic, polyurethane resin that is used as a protective outer wrap over Denso Petrolatum Tapes. This protective coating offers exceptional mechanical and impact strength and the aliphatic polyurethane provides UV stability.

### Uses

- Protective outerwrap for underwater pipes and piles
- Protective outerwrap for underground pipes and piles
- Protective outerwrap for aboveground pipes and piles

### Features

- Resists cold and hot temperatures
- Easy to apply, no mixing or messy clean up
- Resistant to water, acid, salts, or soil organics
- Can be applied underwater or to wet surfaces
- Minimal surface preparation required
- Quick, long-term protective coating, ready for immediate service
- Contains no solvents
- Can be top coated for aesthetics
- UV Resistant

### Surface Prep

Prepare surfaces by removing all loose scale, rust or other foreign matter in accordance to SSPC SP2 "Hand Tool Cleaning" or SP3 "Power Tool Cleaning". High pressure water wash of 3,000 - 7,000 psi (20.68 - 48.26 MPa) is also suitable.

### Application

Spirally wrap a layer of Denso Petrolatum Tape with a minimum 1" (25 mm) overlap. For severely corrosive environments, a 55% overlap is recommended. While wrapping, press air pockets out and smooth all lap seams. Using rubber gloves,



# TECHNICAL DATA SHEET

remove the Denso Glass Outerwrap UV from the hermetically sealed foil pouch and soak in temperate water (salt or fresh) for 20 to 30 seconds. Remove from water and begin wrapping product tightly on substrate, overlapping a recommended 50%.

Irregular surfaces such as valves, flanges, etc. may require the use of Densyl Mastic or Denso Profiling Mastic prior to product application to transition diameter variations. Refer to the product sheets for these specific products for information on application and selection.

A final temporary double layer of Denso Poly-Wrap shall be immediately applied over the uncured Glass Outerwrap UV. This allows all seams of the Glass Outerwrap to lay out more smoothly and provides a tighter cured seal. The Poly-Wrap should be removed after approx. 1 to 2 hours depending on temperature.

## Storage

6 months when stored in original packaging @ 41°F (5°C) to 90°F (32°C). Do not store in direct sunlight.

## Cleaning

Remove any resin immediately from any contaminated surface using a clean, dry cloth. If a solvent is required, use xylene or dibasic ester or comparable solvent containing essentially no water.

## Health & Safety

Refer to SDS before use. Always refer to project specifications as they may supersede Denso specifications.

## Packaging

Tape Width	Tape Length	Rolls*/ Case	Coverage with 50% Overlap
in.	ea.	ea.	ea.
3" (75 mm)	9' (2.7 m)	15	17 ft <sup>2</sup> /case (1.6 m <sup>2</sup> /case)
4" (100 mm)	30' (9 m)	5	25 ft <sup>2</sup> /case (2.3 m <sup>2</sup> /case)
8" (200 mm)	40' (12 m)	3	40 ft <sup>2</sup> /case (3.7 m <sup>2</sup> /case)

\*Other widths and lengths available upon special request.

# Denso Glass Outerwrap UV™

## TECHNICAL DATA

PROPERTIES	ENGLISH	METRIC
Thickness	11 mils avg.	0.28 mm
Flexural Strength (ASTM D790-71)	16,100 psi	113,200 Kgs/mm <sup>2</sup>
Tensile Strength (ASTM D638)	24,900 psi	175,071 Kgs/mm <sup>2</sup>
Compression Strength (ASTM D695-77)	26,600 psi	187,024 Kgs/mm <sup>2</sup>
Dielectric Strength	16,060 volts	16,060 volts
Maximum Service Temperature	250°F	121°C
Setting Time		
@ 50°F (10°C)	16 hours	16 hours
@ 70°F (21°C)	8 hours	8 hours
@ 90°F (32°C)	4 hour	4 hour
Color	Gray, Black or Brown	



DENSO NORTH AMERICA

### LIBERTY SALES & DISTRIBUTION

Hatfield & Washington, PA

Ph: (877) 373-0118 Fx: (888) 850-3787

[sales@libertysales.net](mailto:sales@libertysales.net) [www.libertysales.net](http://www.libertysales.net)

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.