

DENSO OUTERARMOUR

Liquid Epoxy Topcoat

Description

Denso OuterArmour is a two component 100% solids liquid epoxy coating. It is a tough/durable topcoat that provides excellent abrasion resistance and flexibility for Denso FB 30 Tape and Denso Glass Outerwrap.

Uses

- Flexible and durable
- Can be brush, roller or Denso applicator pad applied
- Provides excellent resistance to water, acids, alkalis, salts and mild solvents
- High impact resistance
- Can be applied in one coat up to 40 mils

Application

Surface to be top coated shall be clean, dry and free on any dust, dirt or foreign matter. Mix each of the base and hardener to an even consistency. Pour Part B (Hardener) into Part A (Base) and mix until an even color is achieved while ensuring all sides and the bottom of the container are scraped. Immediately begin applying mixed material onto the Denso FB 30 Tape or Denso Glass Outerwrap by brush or roller while maintaining a wet film thickness of 20-30 mils.



Denso OuterArmour

TECHNICAL DATA

PROPERTIES	VALUE
Solids By Weight	100%
Color	White & Black
Components	Two
Gloss	Semi-Gloss
Mixing Ratio (By Vol.)	1 to 1
Weight/Gallon (Mixed)	11.8 lbs.
Pot Life @ 77°F (100 Grams)	30 minutes
Theor. Coverage @ 40 mils	40 sq. ft./gal.
Recommended Dry Film Thickness	Min. 20 mils
Application Temperature	Min. 50°F (10°C)
Service Temperature	-30°F (-34°C) to 158°F (70°C)
Dry Time @ 77°F:	
To Touch	2 hours
To Handle	4 hours
To Recoat	2 to 4 hours

STORAGE: Store in a dry, well ventilated area. Shelf life 2 years.

HEALTH & SAFETY: Wear protective clothing and ensure adequate ventilation. Avoid contact with skin and eyes. See material safety data sheet.

PACKAGING: Supplied in 2 liter kits.

Liberty Sales and Distribution, LLC

2880 Bergey Road, Suite F

Hatfield, PA 19440

Phone: (877) 373-0118

Fax: (888) 850-3787

Email: sales@libertysales.net



A Member of Winn & Coales International

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.