

PROTAL ST EPOXY MASTIC

Surface Tolerant Liquid Epoxy Glass Flake Coating

Description

Protal ST Epoxy Mastic is a two part, high solids, fast drying, glass flake epoxy coating for application directly onto wire brushed rusty steel substrates to SSPC-SP2/3. Its good penetration and adhesive properties ensure excellent protection in long term exterior exposure.

Uses

Used wherever steel grit blasting is not possible. Protal ST Epoxy Mastic can be used alone or in combination with other topcoats for long term exposure to water in applications such as: structural steel, pipe externals, pipe racks, tanks, offshore platforms, locks, gates, and bridges.

Features

- Minimal surface preparation (SSPC-SP2/3)
- Long term exterior protection
- Excellent water/sea water resistance
- Good resistance to acids and alkalis
- Does not shield cathodic protection
- Good flexibility, hardness and adhesion
- Good impact resistance
- Low VOC's

Application

Prepare surfaces by removing all loose scale, rust or other foreign matter in accordance to SSPC-SP2 "Hand Tool Cleaning" or SP3 "Power Tool Cleaning". High pressure water wash of 3,000 - 7,000 psi (20.68 - 48.26 MPa) is also suitable. This can be achieved using power brushing or machine grinding. If the surface is severely corroded, chipping hammers and needle guns will be required. The surface should finally be cleaned with a vacuum cleaner, clean dry with compressed air or a clean brush. The steel should then have a faint metallic sheen. Use as supplied in pre-weighed packs Part A (base component) with Part B (hardener). Pour all of Part B into Part A and thoroughly mix with a power whip for at least 2 minutes.

The substrate temperature must be a minimum of 5°F (3°C) above the dew point temperature before proceeding with the coating operation. The first coat can then be applied by brush or spray to a wet film thickness of 10 mils / 254 microns (8 mils / 203 microns DFT). Check the film thickness of the coating regularly with a wet film gauge during application. Minimum wait time for overcoating is 4 hours at 77°F (25°C).

Spraying is carried out using a 68:1 airless spray pump and a 21 to 31 thousands of an inch tip. Below 59°F (15°C) add 5% MEK. Apply the second coat at 10 mils (254 microns) wet film thickness in the same manner as the first. When dry, a final weather resistant top coat such as a water based acrylic or polyurethane can be applied by brush or spray.



Protal ST Epoxy Mastic

TECHNICAL DATA

PROPERTIES	VALUE
Pot Life @ 77°F (25°C) (ASTM D2196)	1 hour
Touch Dry @ 77°F (25°C) (ASTM D1640)	3 hours
Theoretical Wet Film Thickness (typical)	10 mils per coat
Theoretical Coverage	163 ft ² /gallon @ 10 mils (4 m ² /liter @ 254 microns)
Solids by Volume	87%
Mixing Ratio by Volume	2 Parts Base:1 Part Hardener
Application Temperature	-20°F to 125°F (-29°C to 52°C) <i>Note: If temperature falls below 50°F (10°C), surface must be preheated.</i>
Service Temperature	-20°F to 150°F (-29°C to 65°C)
Dry Film Thickness	
First coat Denso Protal ST	8 mils (DFT) / 203 microns
Second coat Denso Protal ST	8 mils (DFT) / 203 microns
Final coat acrylic, enamel or polyurethane	2 mils (DFT) / 50.8 microns
Overcoating Time (min.) (ASTM D3359B)	
50°F (10°C)	12 hours
60°F (16°C)	8 hours
77°F (25°C)	4 hours
95°F (35°C)	2 hours
Shore D Hardness @ 77°F (25°C)	85
Adhesion to Steel (ST2) (Elcometer pulloff)	1,800 psi (12.41 MPa)
Hot Salt Fog @ 95°F (35°C) (ASTM B117)	1500 hours
Humidity Test @ 104°F (40°C) w/100%	1500 hours
Color	Light Gray

STORAGE: Store the containers in a dry, well ventilated area. The containers should be kept tightly sealed. Shelf life: 12 months, when stored between 40°F - 100°F (4°C - 38°C).

CLEANING: Clean equipment with MEK or equivalent solvent cleaner.

HEALTH AND SAFETY: Spray or brush under well ventilated conditions. Wear suitable protective clothing and glasses. See material safety data sheet.

PACKAGING: 0.5 (1.9 liter) gallon kits. Other package sizes are available upon request.



Liberty Sales & Distribution, LLC
2880 Bergey Road, Suite F, Hatfield, PA 19440
Phone: (877) 373-0118 Fax: (888) 850-3787
Email: sales@libertysales.net Web: www.libertysales.net

A Member of Winn & Coales International

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.