

Wrapid Sleeve™

One-piece protective sleeve with pre-attached closure

Product Description



Canusa Wrapid Sleeves™ are shipped pre-cut with a pre-attached closure. The adhesive is protected from contamination by an inner liner.

Equipment List



Propane tank, hose, torch & regulator; Appropriate tools for surface abrasion; Knife, roller, rags & approved solvent cleanser; Digital thermometer with suitable probe; Standard safety equipment; gloves, goggles, hard hat, etc.

Surface Preparation and Pre-Heat Chart


3			Surface Preparation					
Standard Sleeves			SIS Standard		SSPC Standard		Min. Pre-Heat Temp.	
			Minimum	Preferred	Minimum	Preferred	°C	°F
	KLC	ктс	St2	Sa2	SP2	SP6	60	(140)
Mastic	KLS	KTS	St2	Sa2	SP2	SP6	65	(150)
2	KLO	кто	St2	Sa2	SP2	SP6	75	(167)

^{*} KTON/KLON is marketed in Canada as K-60 UV


Flame Intensity & Torch Size



Surface Preparation



Ensure that the PE coating edges are beveled to 30°. Clean exposed steel and adjacent pipe coating with a solvent cleanser to remove the presence of oil, grease, and other contaminants.




Ensure that the pipe is dry before cleaning. Prepare the steel joint area using the Surface Preparation and Pre-Heat Chart as a guideline. Lightly abrade the pipe coating adjacent to the cutback area to a distance of 50mm (2") beyond each end of the sleeve width.



Wipe clean or air blast the steel and pipe coating to remove foreign contaminants.

Pre-Heat




Pre-heat the joint area to the minimum required temperature (see Surface Preparation & Pre-Heat Chart). Using a temperaturemeasuring device, ensure that the correct temperature is reached on the steel and at least 50mm (2") on each side of the sleeve.

Sleeve Installation




Partially remove the release liner and gently heat the underlap approximately 150 mm (6") from the edge.




Centre the sleeve over the joint so that the sleeve overlaps between the 10 and 2 o'clock positions. Press the underlap firmly into place.


Sleeve Installation




Remove the remaining release liner.




Wrap the sleeve loosely around the pipe, ensuring the appropriate overlap. Gently heat the backing of the underlap and the adhesive side of the overlap.




Press the closure firmly into place.




Gently heat the closure and pat it down with a gloved hand. Repeating this procedure, move from one side to the other. Smooth any wrinkles by gently working them outward from the centre of the closure with a roller.




Using the appropriate torch, begin at the centre of the sleeve and heat circumferentially around the pipe. Use broad strokes. If utilizing two torches, operators should work on opposite sides of pipe.




Continue heating from the centre toward one end of the sleeve until recovery is complete. In a similar manner, heat and shrink the remaining side.



Shrinking has been completed when the adhesive begins to ooze at the sleeve edges all around the circumference. Finish shrinking the sleeve with long horizontal strokes over the entire surface to ensure a uniform bond.



While the sleeve is still hot and soft, use a hand roller to gently roll the sleeve surface and push any trapped air up and out of the sleeve, as shown above. If necessary, reheat to roll out air.



Continue the procedure by also firmly rolling the closure with long horizontal strokes from the weld outwards.

Inspection



Visually inspect the installed patch for the following:

- Sleeve is in full contact with the steel ioint.
- Adhesive flows beyond both sleeve edges.
- No cracks or holes in sleeve backing.

Storage & Safety Guidelines

To ensure maximum performance, store Canusa products in a dry, ventilated area. Keep products sealed in original cartons and avoid exposure to direct sunlight, rain, snow, dust or other adverse environmental elements. Avoid prolonged storage at temperatures above 35°C (95°F) or below -20°C (-4°F). Product installation should be done in accordance with local health and safety regulations.

These installation instructions are intended as a guide for standard products. Consult your Canusa representative for specific projects or unique applications.

Canusa-CPS A division of ShawCor Ltd.

Head Office

25 Bethridge Rd. Toronto, ON M9W 1M7 Canada

Tel: +1 416 743 7111 Fax: +1 416 743 5927

Canada

Suite 3200, 450 - 1st Street S.W. Calgary, AB T2P 5H1 Canada

Tel: +1 403 218 8207 Fax: +1 403 264 3649

Americas

2408 Timberloch Place, Building C-8 The Woodlands, TX 77380 USA

Tel: +1 281 367 8866 Fax: +1 281 367 4304

Europe, Middle East, Africa & Russia

Unit 3, Sterling Park, Gatwick Road, Crawley, West Sussex RH10 9QT United Kingdom

Tel: +44 1293 541254 Fax: +44 1293 541777

Asia-Pacific

101 Thomson Road, #11-03 United Square 307591 Singapore

Tel: +65 6749 8918 Fax: +65 6749 8919

Canusa-CPS is registered to ISO 9001:2008

Canusa warrants that the product conforms to its chemical and physical description and is appropriate for the use stated on the installation guide when used in compliance with Canusa's written instructions. Since many installation factors are beyond our control, the user shall determine the suitability of the products for the intended use and assume all risks and liabilities in connection therewith. Canusa's liability is stated in the standard terms and conditions of sale. Canusa makes no other warranty either expressed or implied. All information contained in this installation guide is to be used as a guide and is subject to change without notice. This installation guides supersedes all previous installation guides on this product. E&OE

Part No. 99060-010 IG_Wrapid Sleeve_rev015

Backfilling Guidelines

After shrinking is complete, allow the sleeve to cool for 2 hours prior to lowering and backfilling. To prevent damage to the sleeve, use selected backfill material, (no sharp stones or large particles) otherwise an extruded polyethylene mesh or other suitable shield should be used.

