

Royston®

Technical Data Sheet

DESCRIPTION	<p>Royston Thick N' Quick Mastic is a thixotropic, brush applied asphalt coating for below grade applications. Thick N' Quick is a time proven coating technology for providing corrosion protection to metal fittings, flanges, valves, tanks, mechanical couplings, anode connections and other difficult and irregular configurations.</p> <p>Thick N' Quick easy to apply by brush or rubber glove. Due to its thixotropic nature it resists drips and sags during application, but will become more flowable the more it is mixed.</p>
RECOMMENDED USE	Appropriate for coating fittings, flanges, valves, tanks, mechanical couplings, anode connections and other difficult and irregular configurations.
SUBSTRATE COMPATIBILITY	Steel, Stainless Steel, Ductile Iron, other metals, FBE, CTE, Asphalt, Concrete
SURFACE PREPARATION	SSPC SP-2 Hand Tool Cleaning, SSPC SP-3 Power Tool Cleaning or SSPC SP-6/ NACE No. 3 Commercial Blast Cleaning
PRIMER	None needed
OPTIONAL REINFORCEMENT	Royston Glas-Wrap can be applied over the mastic or between mastic layers, giving the coating added strength and impact resistance.
SAFETY	Refer to Safety Data Sheet: SDS-TNQ
APPLICATION	<p>Apply in two or three coats that each have a WFT of 20 mils. Allow the first coat to dry to the touch before application of the second coat, about 30 minutes. Never apply more than 40 mils in a single coat to prevent mud cracking.</p> <p>Thick N' Quick is usually sufficiently dry after 1 1/2 hours for light handling and backfilling. Low temperature or high humidity conditions will lengthen the dry time.</p> <p>Refer to Application Guideline: AG-MASTICS for detailed more information.</p>

The information contained here is provided for product selection purposes only and is not to be considered specification or performance data. Under no circumstance will the seller be liable for any loss, damage, expense or incidental or consequential damage of any kind arising in connection with the use or inability to use its product. Specific conditions of sale and Chase's limited warranty are set out in detail in Chase Corporation Terms and Conditions of Sale. Those Terms and Conditions are the only source that contain Chase's limited warranty and other terms and conditions.

Chase Corporation
An ISO 9001:2008
REGISTERED COMPANY

Typical Technical Data

Property	US Customary	Metric	Test Method
Color	Black	Black	
Percent Solids, Volume	64%	64%	ASTM D2697
Percent Solids, Weight	74%	74%	ASTM D2369
Solvents	Toluene, VM&P Naphtha	Toluene, VM&P Naphtha	
VOC Content	<2.3 lb/gal	< 280 g/l	
Flash Point	38 °F	3 °C	ASTM D327 (Closed Cup)
Water Absorption	<0.5%	<0.5%	ASTM D570
Water Vapor Transmission Rate	<0.5 g/(h*m ²)	<0.5 g/(h*m ²)	ASTM E96 Procedure B
Holiday Detection Setting	2000V for 15 mil DFT	2000V for 380 µm DFT	NACE SP0188
Cathodic Disbondment, 30 days	<1.1 in ²	<15 mm radial	ASTM G8
Service Temperature Range	-40 °F to +250 °F	-40 °C to +121 °C	

ORDERING INFORMATION

Container Size	Containers Per Case	Weight
1 Gallon	4	43# per Case

Liberty Sales & Distribution, LLC

2880 Bergey Road, Suite F, Hatfield, PA 19440

Phone: (877) 373-0118 Fax: (888) 850-3787

Email: sales@libertysales.net Web: www.libertysales.net