



Tapecoat[®]

Technical Data Sheet

DESCRIPTION

Tapecoat TR Green is 35 mil, cold applied coating designed to provide protection against corrosion and electrolysis on below grade metal substrates. Combined with strong, flexible film backing, Tapecoat TRGreen provides a protective coating with cohesive strength and durability that conforms well to irregular shapes.

Tapecoat TR Green has an integrated primer; the primer is in the adhesive. This exclusive formulation allows for faster application as there is no need to apply a separate primer when application temperatures are above 40° F. The Tapecoat TR Green coating system is VOC free when applied without a primer. When used with Tapecoat Omniprime[®] the coating system will meet even the strictest environmental laws.

RECOMMENDED USE

The flexible backing makes it a good coating for hand wrapping. Appropriate for coating and reconditioning small to moderate diameter pipe, bends, tees and metal structures, as a single component coating below grade.

SUBSTRATE COMPATIBILITY

Steel, Stainless Steel, Ductile Iron, other metals, FBE, PE, PP

SURFACE PREPARATION

SSPC SP-2 Hand Tool Cleaning, SSPC SP-3 Power Tool Cleaning or SSPC SP-6/ NACE No. 3 Commercial Blast Cleaning

OPTIONAL PRIMER

Tapecoat TR Green has an integrated primer to allow for quick, easy and permanent adhesion. When required by the job specification or when application temperatures are below 40° F, a 4 mil WFT of Tapecoat Omniprime may be applied to the pipe surface to ensure the required bond.

REFERENCE

Tapecoat TR Green meet all of the performance criteria listed in the most recent revisions of:

NACE SP0109 (Cold-Applied Laminate Polymeric Tapes)
ANSI/AWWA C209 (Type II)

SAFETY

Refer to Material Safety Data Sheet: MSDS-TC-GRAY

APPLICATION

Refer to Application Guidelines: AG-COLD-APPLIED-ELASTOMERIC-TAPE

The information contained here is provided for product selection purposes only and is not to be considered specification or performance data. Under no circumstance will the seller be liable for any loss, damage, expense or incidental or consequential damage of any kind arising in connection with the use or inability to use its product. Specific conditions of sale and Chase's limited warranty are set out in detail in Chase Corporation Terms and Conditions of Sale. Those Terms and Conditions are the only source that contain Chase's limited warranty and other terms and

Chase Corporation
An ISO 9001:2008
REGISTERED COMPANY

Typical Technical Data

Property	US Customary	Metric	Test Method
Total Thickness	35 mils	0.89 mm	ASTM D1000
Backing Thickness	7 mils	0.18 mm	ASTM D1000
Adhesive Thickness	28 mils	0.71 mm	ASTM D1000
Cathodic Disbondment, 30 days	<0.4 in ² (No Primer)	<10 mm radial (No Primer)	ASTM G8
Adhesion to Primed Steel	10 lb/in	1.75 N/mm	ASTM D1000
Tensile Strength	14 lb/in	2.45 N/mm	ASTM D1000
Elongation	800%	800%	ASTM D1000
Dielectric Strength	Exceeds 12 kV	Exceeds 12 kV	ASTM D149
Holiday Detection Setting	7400 V	7400 V	NACE RP0274
Impact Resistance	20 in lb (double wrap)	2.3 J (double wrap)	ASTM G14
Water Vapor Transmission Rate	<0.005 g/(24h*100 in ²)	<0.003 g/(h*m ²)	ASTM E96 Method B
Water Absorption	<0.5%	<0.5%	ASTM D570
Leachable Chlorides	None	None	
Service Temperature Range	-20°F to +125°F	-29°C to +52°C	

ORDERING INFORMATION

Roll Size	Rolls Per Case
2" x 50'	12
4" x 50'	6
6" x 50'	4

CASE PACKAGING
1.0 SQ (100 ft²) per case
Case Weight: 28 lbs

Liberty Sales & Distribution, LLC

2880 Bergey Road, Suite F, Hatfield, PA 19440

Phone: (877) 373-0118 Fax: (888) 850-3787

Email: sales@libertysales.net Web: www.libertysales.net